

Nominal Ø or Least Thickness or Nominal Wall Thickness (mm)	Tensile Strength (MPa)	Yield Strength at 0.2% Offset (MPa)	Elongation in 4D% (Long.)	Elongation in 4D% (L.T.)	Elongation in 4D% (S.T.)	Reduction of Area % (Long.)	Reduction of Area % (L.T.)	Reduction of Area % (S.T.)
Up to 50.8	931	862	10	10	-	25	20	-
Over 50.8 to 101.60	896	827	10	10	10	25	20	15
Over 101.60 to 152.40	896	827	10	10	8	20	20	15